

## **Macroporous Strong Base Anion Resin D201**

This anion exchange resin is styrene and divinyl benzene copolymer cross linked with quaternary amine[ $-N(CH_3)_3OH$ ]. It is mainly used for demineralization, wastewater treatment, Antibiotic extraction.

## **Characteristics**

Item		D201	
Appearance		Milky white to light yellow beads	
Matrix		Styrene/DVB Macroporous	
Ionic Form		Cl -	
Mass total exchange capacity	mmol/g(dry)	≥ 3.70	
Volume total exchange capacity	mmol/ml	≥ 1.20	
Moisture content	%	50.00 - 60.00	
Bulk density	g/ml	0.65 - 0.73	
Specific density	g/ml	1.06 - 1.10	
Particle size	%	(0.315-1.25mm) ≥ 95.0 (<0.315mm) ≤ 1.0	
Whole Beads Rate	%	≥ 95.0	
Uniformity coefficient		≤ 1.6	

## Packing:

	Woven bags lined with	
	plastic sheets	25L/bag
$\triangleright$	PE valve bags	25L/bag
$\triangleright$	Supersacks	1000L/bag

## Storage:

The recommended storage temperature is 5-40°C. Prohibited exposure, dehydration, contamination.